ROXUL 2 ComfortBatt

Technical Data Sheet

Batt Insulation 07210
Blanket Insulation 07 21 16*

ROXUL COMFORTBATT®

Thermal Batt Insulation

Product Description & Application

ROXUL COMFORTBATT® is a mineral wool batt insulation designed for thermal resistance in wood and steel framing

| | Performance | | Test Standard |
|--------------------|---|--|------------------------------|
| Compliance | Mineral Fiber Thermal Insulation for Buildings, Type 1 Compliant | | CAN/ULC S702 |
| Reaction to Fire | Flame spread index = 0; Smoke developed index = 0 Determination of Non Combustibility of Building Materials - Non Combustible | | CAN/ULC S102 CAN/ULC S114 |
| Density | > 2 lbs/ft³ (>32 kgs/m³) | | ASTM C167 |
| Thermal Resistance | Wood Stud R 14 (RSI 2.47) - 3.5" thick (89mm) R 22 (RSI 3.87) - 5.5" thick (140mm) R 24 (RSI 4.23) - 5.5" thick (140mm) R 28 (RSI 4.93) - 7.25" thick (184 mm) R 32 (RSI 5.64) - 8" thick (203 mm) | Steel Stud R 10 (RSI 1.76) - 2.5" thick (64mm) R 14 (RSI 2.47) - 3.5" thick (89mm) R 22.5 (RSI 3.96) - 6" thick (152mm) R 24 (RSI 4.23) - 6" thick (152mm) | ASTM C518 |
| Dimensions | Wood Stud 16" (406mm) on center: 15.25" x 47" (387mm x1194mm) Wood Stud 24" (610mm) on center: 23" x 47" (584mm x 1194mm) Steel Stud 16" (406mm) on center: 16.25" x 48" (413mm x 1219mm) Steel Stud 24" (610mm) on center: 24.25" x 48" (616mm x 1219mm) | | |



Issued 04-01-16 Supersedes 06-26-13 NOTE: *Mast Format 1995 Edition **Master Format 2004 Edition. As ROXUL Inc has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's products. ROXUL Inc's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.



ROXUL INC 8024 Esquesing Line Milton, On. L9T 6W3 tel: 800-265-6878 fax: 800-991-0110 www.roxul.com